

PML-4EFP★PM-4EFP(general cutting)

Workpiece material	Cast iron, Carbon steel, Alloy steel ~30HRC		Stainless steel		Pre-hardened steel, quenched and tempered steel ~40HRC		Pre-hardened steel, quenched and tempered steel ~50HRC		Hardened steel ~55HRC	
	Diameter (mm)	Rotating speed (min ⁻¹)	Feed speed (mm/min)	Rotating speed (min ⁻¹)	Feed speed (mm/min)	Rotating speed (min ⁻¹)	Feed speed (mm/min)	Rotating speed (min ⁻¹)	Feed speed (mm/min)	Rotating speed (min ⁻¹)
6	7000	1170	3700	210	5300	900	4200	705	3710	510
8	5200	1155	2800	210	4000	885	3200	720	2785	525
10	4200	1140	2200	210	3200	875	2500	680	2230	490
12	3500	1140	1850	210	2650	875	2100	680	1855	490
16	2600	1065	1400	185	2000	815	1600	645	1390	470
20	2050	1045	1100	165	1600	805	1250	630	1115	455

Maximum cutting depth			

Indexable milling tools

Solid carbide end mills

Cutting parameters for PML/PM series end mills

1. The above table shows the standard value of side milling. When milling slot, 50%~70% of rotating speed and 40%~60% of feed speed stated above are recommended as standard.
2. Please select high-precision machine and tool holder.
3. Please use air blow or cutting liquid with high mist retardant property.
4. Down milling is recommended in the case of side milling.
5. When the machine rigidity and workpiece fixture stability is low, vibration and abnormal noise may be generated. Please reduce the rotating speed and feed speed stated above correspondingly.
6. Make overhang of tool as short as possible in conditions of non-interference.

PML-4EFP★PM-4EFP(high speed side milling)

Workpiece material	Cast iron, Carbon steel, Alloy steel ~30HRC		Carbon steel, Alloy steel ~40HRC		Pre-hardened steel, quenched and tempered steel ~45HRC		Pre-hardened steel, quenched and tempered steel ~50HRC		Hardened steel ~55HRC		
Cutting speed	300m/min		250 m/min		200 m/min		150 m/min		100 m/min		
Diameter (mm)	Rotating speed (min ⁻¹)	Feed speed (mm/min)	Rotating speed (min ⁻¹)	Feed speed (mm/min)	Rotating speed (min ⁻¹)	Feed speed (mm/min)	Rotating speed (min ⁻¹)	Feed speed (mm/min)	Rotating speed (min ⁻¹)	Feed speed (mm/min)	
6	15915	2215	13260	1845	10600	1475	7960	1105	5300	740	
8	11935	2210	9950	1820	7960	1470	5970	1080	3980	740	
10	9550	2160	7960	1795	6370	1445	4775	1080	3180	715	
12	7960	2160	6630	1795	5300	1445	3980	1170	2650	715	
16	5970	2010	4975	1680	3980	1340	2985	1170	1990	670	
20	4775	2010	3980	1980	3180	1340	2390	1105	1590	670	
Maximum cutting depth											

1. Please select high-precision machine and tool holder.
2. Please use air blow or MQL (minimum oil mist cooling).
3. Down milling is recommended in the case of side milling.
4. When the machine rigidity and workpiece fixture stability is low, vibration and abnormal noise may be generated. Please reduce the rotating speed and feed speed stated above correspondingly.
5. Make overhang of tool as short as possible in conditions of non-interference.