



ST series twist drills(internal coolant)

3D

5D

Workpiece material	Mild steel HB≤180		Carbon steel, alloy steel ~30HRC		Stainless steel					
					Austenite		Martensite		Ferrite	
Cutting speed	80~150m/min		80~150m/min		40~80 m/min		50~100 m/min		60~120 m/min	
Diameter (mm)	Rotating speed (min ⁻¹)	Feed rate (mm/r)	Rotating speed (min ⁻¹)	Feed rate (mm/r)	Rotating speed (min ⁻¹)	Feed rate (mm/r)	Rotating speed (min ⁻¹)	Feed rate (mm/r)	Rotating speed (min ⁻¹)	Feed rate (mm/r)
3	12700	0.09~0.12	12700	0.09~0.12	6300	0.03~0.07	7400	0.03~0.07	9000	0.03~0.07
4	9600	0.10~0.15	9600	0.10~0.15	4700	0.04~0.08	5600	0.04~0.08	6700	0.04~0.08
5	7600	0.12~0.18	7600	0.12~0.18	3800	0.05~0.10	4500	0.05~0.10	5400	0.05~0.10
6	6400	0.14~0.20	6400	0.14~0.20	3200	0.06~0.12	3700	0.06~0.12	4500	0.06~0.12
8	4800	0.16~0.24	4800	0.16~0.24	2400	0.08~0.16	2800	0.08~0.16	3400	0.08~0.16
10	3800	0.18~0.27	3800	0.18~0.27	1900	0.10~0.18	2200	0.10~0.18	2700	0.10~0.18
12	3200	0.20~0.30	3200	0.20~0.30	1600	0.12~0.20	1900	0.12~0.20	2300	0.12~0.20
14	2700	0.22~0.35	2700	0.22~0.35	1350	0.13~0.22	1600	0.13~0.22	1900	0.13~0.22
16	2400	0.25~0.36	2400	0.25~0.36	1200	0.14~0.25	1400	0.14~0.25	1700	0.14~0.25
18	2100	0.28~0.38	2100	0.28~0.38	1050	0.15~0.28	1200	0.15~0.28	1500	0.15~0.28
20	1900	0.30~0.40	1900	0.30~0.40	950	0.16~0.30	1100	0.16~0.30	1350	0.16~0.30

- When the tool is used for the first time, please do a test cutting with 90% of the cutting speed or 85% of the feed rate stated above. As cutting conditions become stable, gradually increase the cutting speed and feed rate.
- The cutting conditions above are applicable for drilling with emulsion.
- When clamping drill, please use a collet without any defect or dust, and keep the radial run-out of drill under 0.02mm.
- These conditions above are applicable for cutting depth under 5D.

SC series twist drills(external coolant)

3D

5D

Workpiece material	Cast iron		Nodular cast iron		Silicon aluminium alloy				Aluminum alloy	
					Si≤10%		Si>10%			
Cutting speed	50~80m/min		40~70m/min		100~180m/min		80~140m/min		120~200m/min	
Diameter (mm)	Rotating speed (min ⁻¹)	Feed rate (mm/r)	Rotating speed (min ⁻¹)	Feed rate (mm/r)	Rotating speed (min ⁻¹)	Feed rate (mm/r)	Rotating speed (min ⁻¹)	Feed rate (mm/r)	Rotating speed (min ⁻¹)	Feed rate (mm/r)
2	9550	0.06~0.08	8000	0.06~0.08	20000	0.07~0.16	18000	0.07~0.16	24000	0.07~0.16
3	6400	0.09~0.12	5300	0.09~0.12	15000	0.09~0.18	12700	0.09~0.18	16000	0.09~0.18
4	4800	0.10~0.15	4000	0.10~0.15	11000	0.10~0.22	9600	0.10~0.22	12000	0.10~0.22
5	3800	0.12~0.18	3200	0.12~0.18	9000	0.12~0.25	7600	0.12~0.25	10000	0.12~0.25
6	3100	0.14~0.20	2700	0.14~0.20	7400	0.14~0.28	6400	0.14~0.28	8500	0.14~0.28
8	2400	0.16~0.24	2000	0.16~0.24	5600	0.18~0.32	4800	0.18~0.32	6400	0.18~0.32
10	1900	0.18~0.27	1600	0.18~0.27	4500	0.22~0.36	3800	0.22~0.36	5000	0.22~0.36
12	1600	0.20~0.30	1300	0.20~0.30	3700	0.25~0.40	3200	0.25~0.40	4200	0.25~0.40
14	1350	0.22~0.35	1150	0.22~0.35	3200	0.27~0.44	2700	0.27~0.44	3600	0.27~0.44
16	1200	0.25~0.36	1000	0.25~0.36	2800	0.32~0.48	2400	0.32~0.48	3200	0.32~0.48

- When the tool is used for the first time, please do a test cutting with 90% of the cutting speed or 85% of the feed rate stated above. As cutting conditions become stable, gradually increase the cutting speed and feed rate.
- The cutting conditions above are applicable for drilling with emulsion.
- When clamping drill, please use a collet without any defect or dust, and keep the radial run-out of drill under 0.02mm.
- These conditions above are applicable for cutting depth under 5D.